

PRODUCT DATA SHEET

April 1999

Metacaulk® 1200 Spray Applied Mastic

Classified System Numbers
HWD 0032



1. Product Description

Metacaulk® 1200 is a single component, general purpose fire rated sealant for construction joints such as top of the wall, curtain wall perimeter, expansion, control, etc. and for general construction gaps and voids. Metacaulk® 1200 is a latex-based sealant that is designed for spray application and provides a fast, economical means of installation on long joint runs. It cures to an elastomeric membrane seal that is suitable where dynamic movement is expected. In the event of a fire, Metacaulk® 1200 will prevent the spread of flames, smoke, hot gases and water through the joint openings. No dilution or mixing is required for use. Metacaulk® 1200 can be brushed or troweled from the pail or applied with a spray pump. Metacaulk® 1200 systems are rated for up to 2 hour conditions in accordance with the UL 2079 (Tests for Fire Resistance of Building Joint Systems) test standards. Metacaulk® 1200 has been cycled 500 times, meeting the new ASTM E 1399 standard.

Use Metacaulk® 1200 for various applications:

Top of the Wall Construction Joints

Deflection Track Wall Systems

For complete list of product applications or for additional technical information, call RECTORSEAL for the latest updated information.

Metacaulk® 1200 Features

- Sprayable, Brushable or Trowelable
- Latex-based
- Flexible - Elastomeric
- Paintable
- VOC Compliant
- Safe and Easy to Use
- Minimum 2 Year Shelf Life

2. Material Properties

Asbestos Fillers	None
Solvents	None
Hazardous Ingredients	None
Application	Spray, Brush or Trowel
Color	Red
Cure Time	5 to 7 days (1/8" at 77°F)
Density	9.0+/- 0.3 lbs./gal.
Viscosity	120,000 to 150,000 cps
Flexible	Yes
Skin Over Time	30 - 45 min. (at 77°F)
pH Value	7 to 8
Volume Coverage:	
Per Square Foot	18 ³ "
Per Gallon	12.8 sq. ft.
For 5 gallons	1155 cu. in.
VOC	Negligible



3. Applications

Metacaulk® 1200 can be used as a general purpose fire rated sealant and smoke seal for construction joints on both vertical and horizontal surfaces. Metacaulk® 1200 is also an excellent fire rated acoustical sealant and can be used in areas under constant vibration or movement.

4. Installation Data

Tightly pack with the appropriate backing material as listed in the selected UL System design. There should be no loose insulation, voids or gaps present. Spray the required coating thickness to completely cover mineral wool and overspray a minimum 1/2" beyond on all surrounding surfaces.

For Metacaulk® 1200 application, use recommended spray equipment. Contact Technical service at 1-800-231-3345 for current recommendations.


When system clean up is needed, follow manufacture's instructions for specific equipment used.

NOTE: SPRAY EQUIPMENT CAN BE DANGEROUS! USE ONLY PROPERLY TRAINED PERSONNEL. FOLLOW ALL SAFETY AND OPERATION INSTRUCTIONS AND PROCEDURES.

5. Testing Data

Metacaulk® 1200 has been listed by UL Listed System Numbers are HWD 0032. Additional listings can be obtained by calling RECTORSEAL. For specific test criteria, refer to the UL Fire Resistance Directory or call RECTORSEAL.

Metacaulk® 1200 was tested at positive pressure with a minimum 0.01 inches (2.5 Pa) water and in accordance with UL 2079.



6. Storage & Handling

Metacaulk® 1200 should be stored in unopened container between 35° and 120°F to obtain a minimum 2 year shelf life. NOTE: Do not dilute; no mixing is required. Keep from freezing. Keep products stored under protective cover in original containers.

7. Availability

Metacaulk® 1200 is available in 5 gallon pails.

8. Limitations

Metacaulk® 1200 is not designed to be used in areas under continuous immersion or in areas which would be continuously wet. Metacaulk® 1200 should not be used on hot uninsulated surfaces above 200°F.

9. Cautions

FOR CHEMICAL EMERGENCY, SPILL, LEAK, FIRES, EXPOSURE OR ACCIDENT, CALL CHEMTREC - DAY OR NIGHT 1-800-424-9300.

PRECAUTIONS: Do not take internally. May be harmful if swallowed. May cause eye and skin irritation. Wear gloves and safety glasses. Wash after handling. **FIRST AID:** For any overexposure or if skin irritation develops get immediate medical attention. **Eyes** - Flush 15 minutes with clean water. **Skin** - Wash with soap and water. **Ingestion** - Call physician immediately **SPILLS:** Clean up immediately with scrapers and water. **STORAGE AND HANDLING:** Keep container upright and tightly closed. Do not reuse empty container. **KEEP OUT OF REACH OF CHILDREN.**

For additional information, refer to Material Safety Data Sheet.

For additional technical service,
call: 713-263-8001 or 1-800-231-3345
fax: 713-263-7577 or 1-800-452-2824

RECTORSEAL
2601 SPENWICK DRIVE HOUSTON, TEXAS 77055
WWW.RECTORSEAL.COM
WWW.METACAULK.COM

10. LIMITED WARRANTY

RectorSeal makes the Limited Express Warranty that at the date of delivery this product will be free from defects in RectorSeal materials and workmanship. THIS LIMITED EXPRESS WARRANTY IS EXPRESSLY IN LIEU OF ANY OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, AND OF ANY OTHER OBLIGATION ON THE PART OF RECTORSEAL. The sole remedy for breach of the Limited Express Warranty shall be the refund of the purchase price. All other liability is negated and disclaimed, and RectorSeal shall not be liable for incidental or consequential damages.

Suggestions and recommendations covering the use of our products are based on our past experience and laboratory findings. However, as we have no control as to the methods and conditions of application, we only assume responsibility for the uniformity of our products within manufacturing tolerances.

METACAULK® 1200 COVERAGE RATE:

NOTE: Coverage rates as given are mathematical calculations. Allow for application losses, opening size variations and applied thickness variations. (Verify all calculations)

Based on 3" fluted metal deck with 3/4" relief joint.

Opening Width (inches)	*Coverage Rate in Lineal Feet Per Gallon at Application Thickness of: 1/8 inch
1/2	102
3/4	88
1	77
1 1/2	61
2	51
2 1/2	44
3	38
3 1/2	34
4	30
5	25
6	22

* Calculation includes 1/2" overlap along both edges of opening